Stamskin



	stamskin
Available for the branches	dental medical industry office
Composition	Stamskin TOP F 4340, under layer polyamide jersey, coating antibacterial and antifungal treatment.
Weight	780 g/m2
Light fastness	Scale 7
Abrasion resistance	120.000 (rubs) Martindale.
Cleaning	With brush, water and soap, rinse of with water, do not clean with stain-removers containing solvents or oily products.
Characteristics	 PVC-based leatherette Urine, blood, sweat and mould resistant Contains Folpet (N0528 / 2012 / CE-Folpet) Water resistant, antibacterial, antifungal and fire retardant Wear resistant
Additional information	Contains Folpet (N0528 / 2012 / CE-Folpet); an antifungal additive used to help maintaining appearance, physical properties and to prolong service life of the products.
Fire resistance	EN 1021 1-2, D: DIN 53438/T2, F: NFP 92.507

